

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 407 004 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 90304243.0

(51) Int. Cl.⁵: **C08F 299/06, C09D 175/16,
G02B 5/00**

(22) Date of filing: 20.04.90

(30) Priority: 27.06.89 US 371833

(43) Date of publication of application:
09.01.91 Bulletin 91/02

(34) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IT LI LU NL SE

(71) Applicant: **Borden, Inc.**
180 East Broad Street
Columbus Ohio 43215(US)

(72) Inventor: **Duecker, David Clarke**
4714 Greenlee Avenue
Cincinnati, Ohio(US)

(74) Representative: **Wilkinson, Stephen John et al**
c/o Stevens, Hewlett & Perkins 5 Quality
Court Chancery Laneane
London WC2A 1HZ(GB)

(54) **Radiation-curable matrix material, optical fiber ribbons containing same; and process for preparing said optical fiber ribbons.**

(57) A radiation-curable matrix material for affixing coated and inked optical fibers in a ribbon configuration is disclosed. The material comprises an aliphatic polyether based urethane acrylate; a monomer having a plurality of acrylate or methacrylate moieties; an alkyl acrylate or methacrylate; and an optional photoinitiator. Also disclosed are an optical fiber ribbon prepared therefrom; a process for preparing such ribbon; and a radiation-curable coating composition generally applicable for coating a substrate.

EP 0 407 004 A2

RADIATION-CURABLE MATRIX MATERIAL; OPTICAL FIBER RIBBONS CONTAINING SAME; AND PROCESS FOR PREPARING SAID OPTICAL FIBER RIBBONS

BACKGROUND OF THE INVENTION:

The present invention relates to radiation-curable compositions useful as matrix material for optical fiber ribbons; to optical fiber ribbons containing such matrix material; and to processes for preparing such matrix-containing ribbons.

Optical glass fibers have revolutionized the telecommunications industry. The result has been a tremendous growth in demand for optical fibers which are free of many of the inherent defects of glass fibers.

Immediately after drawing, glass fibers are exceptionally strong and have very few intrinsic defects. However, such pristine fibers are very easily flawed by exposure to environmental conditions including dust and moisture. Therefore, there have been developed in the prior art numerous coatings which are minimally capable of protecting the underlying glass fiber from external harmful forces and which optimally possess properties rendering them capable of obviating one or more of the various potential problems which may deleteriously effect optical fiber performance. Such properties include, *inter alia*, a glass transition temperature rendering the fiber useful over a large potential temperature use range; a higher refractive index than that of the fiber to refract any errant light signals away from the fiber; rapid cure, e.g., under ultraviolet irradiation; and high impermeability to moisture which may damage the coating or the fiber itself and may cause delamination of the two. Additionally, the adhesion level between the fiber and the coating must be optimized so that the coating will remain adhered to the fiber during use but be easily stripped therefrom, with minimal damage to the integrity of the fiber and the coating, so that the fibers may be easily spliced in the field. Above all, the fiber coatings should display good thermal, oxidative and hydrolytic stability, to protect the underlying fiber over the long term, i.e., over twenty-five years' time.

In certain applications, such as in short haul, fiber-to-the-home uses, a single, coated optical fiber may adequately transmit a signal from one point to the next. However, in most embodiments, a relatively large number of fibers are necessary to transmit a large volume of signals. For example, in the telecommunications industry, aggregates of fibers spanning oceans or continents and containing dozens of individual fibers may be required. Fibers are conveniently aggregated into cables, wherein large numbers of coated optical fibers are laid in parallel and are protected by a common sheathing material such as a layered arrangement which may include fiberglass, steel tape and reinforced rubber cabling material.

In numerous individual coated optical fibers are aggregated into a cable, it is necessary to be able to identify each of the individual fibers. For example, when two cable segments are to be spliced together, it is necessary to splice together ends of each like optical fiber in order for a signal to convey properly. When only a few fibers are contained in a cable, identification may be adequately made by having the coating of each individual fiber be a characteristic color; thus the splicer may simply match up green fiber to green fiber, red to red, and so forth.

However, when the cable contains one hundred or more fibers, it may become impracticable to use a sufficient number of distinctive inks as to color each fiber distinguishably. Thus, a geometric means of distinguishing each fiber is used. For example, arranging the fibers in a number of layers, each layer containing perhaps twelve ink-coated fibers of different respective colors, will greatly facilitate the task of matching up fibers when splicing.

One practical way by which such spatial ordering of numerous fibers may be accomplished is to create two-dimensional fiber arrays, wherein fibers are situated in a generally planar arrangement, within a given array, with the fibers in the array disposed in parallelism with each other. These arrays are stacked one atop another in a three dimensional structure.

Such arrays are known in the art as ribbons. For example, it is known to prepare a two-dimensional ribbon by forming a "sandwich" of parallel coated optical fibers between two sheets of adhesive-coated Mylar tape, thus affixing the fibers in that configuration. This "sandwich" provides structural integrity and a tack free exterior surface.

However, this arrangement is less than optimal because the tape occupies a substantial proportion of the total volume of the sandwich, so that when several "sandwiches" are stacked to form a cable, an undesirably high proportion of the total cable volume is taken up by tape (rather than by optical fiber).

Thus it has been envisioned to prepare an optical fiber ribbon having a matrix material in which the optical fibers are embedded in the desired generally planar, parallel arrangement. This matrix material should, *inter alia*, have suitable glass transition temperature; cure rapidly; be non-yellowing; and have high

thermal, oxidative and hydrolytic (moisture) stability.

Additionally, the matrix material must be adherent enough to the coated, colored optical fibers to prevent separation of the fibers during processing into cables, but not so adherent as to remove the ink coloration from the individual ink-colored fibers when the matrix material is stripped from the fibers to permit splicing. Removal of the ink from a coated, colored optical fiber is referred to in the industry as "breakout failure"; it makes identification of the individual fibers impossible.

Furthermore, the matrix material must possess solvent resistance, inasmuch as, in the field, splicers typically remove residual matrix and coating material from stripped fibers using a solvent such as trichloroethane or ethanol. Matrix material on an unstripped fiber should not absorb solvent and swell and thus compromise the integrity of ribbon.

SUMMARY OF THE INVENTION:

Accordingly, the invention provides, in one embodiment, a radiation-curable matrix material for affixing coated and ink-colored optical fibers in a ribbon configuration. The matrix material generally comprises:

- (a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;
- (b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties per monomer molecule;
- (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms; and
- (d) from about 0 percent to about 10 percent by weight of a photoinitiator, all of the percentages by weight being based on the total weight of (a), (b), (c) and (d).

In preferred embodiments, the polyether-based urethane acrylate is silicone modified; and the matrix material additionally comprises a stabilizer, is ultraviolet curable and comprises at least about 1 percent by weight of the photoinitiator.

In an alternate embodiment, the material includes from about 1 percent to about 30 percent of an adhesion increasing compound such as a polyester-based aliphatic urethane acrylate oligomer in addition to the alkyl-containing acrylate-functional monomer (c).

In another embodiment, then, the invention is a process for adjusting the adhesive bond of a cured matrix material to glass optical fibers which are coated with a coating comprising a cured acrylate-or methacrylate-containing coated composition and colored by the application of inks of different respective colors for fiber identification, by incorporating into an uncured matrix material as described above a component that is capable of increasing the adhesive bond.

In another embodiment, the invention is an optical fiber ribbon assembly comprising a plurality of coated, colored optical fibers in a fixed relationship, e.g., a generally planar, generally parallel arrangement, and a radiation-cured matrix material bonding said fibers in said position within the matrix material. The matrix material has sufficient adhesion to the fibers to remain adhered thereto during use but is easily strippable therefrom. Specifically, the invention may be such an optical fiber ribbon wherein the matrix material is as described above.

In yet another embodiment, the invention is a process for preparing an optical fiber ribbon. The process comprises mechanically aligning the optical fibers in the desired (e.g., generally parallel) arrangement; applying about the fibers the matrix material described above; and curing the matrix material to secure the fibers in the desired arrangement, e.g., preferably with ultraviolet light or an electron beam.

In a still further embodiment, the invention is a coating composition for coating a substrate, the composition being as described above.

DESCRIPTION OF THE PREFERRED EMBODIMENTS:

RADIATION CURABLE MATRIX MATERIAL

The invention relates in part to a radiation-curable matrix material, e.g., for affixing coated and inked optical fibers in a ribbon or other desired configuration. The cured matrix material should have, inter alia, the following properties: moisture resistance; solvent resistance; ease of stripping; resistance to breakout failure; low volatiles content; fast cure when irradiated; and long term thermal, oxidative and hydrolytic

stability. It should be non-yellowing. It should also be resistant to failure during "cabling". Cabling is the term used to describe a process of gathering a plurality of the ribbons together to form a cable.

The matrix material contains at least three basic ingredients, and, if envisioned for ultraviolet cure, at least four:

- 5 (a) a polyether-based urethane acrylate;
- (b) a monomer having a plurality of acrylate or methacrylate groups;
- (c) an alkyl acrylate or an alkyl methacrylate monomer; and
- (d) optionally, for a U.V.-curable composition, a photoinitiator.

10

(A) The Polyether-Based Urethane Acrylate

The first ingredient is a specific urethane acrylate. Specifically, it is based on an aliphatic polyether polyol, which is reacted with an aliphatic polyisocyanate and acrylated.

- 15 In a preferred embodiment, this component is an oligomer which is silicone-modified, e.g., it may have silicone coreacted into the polyether portion of the backbone. The silicone-modified alternative may provide the most desirable release characteristics vis-a-vis the ink (i.e., may exhibit less adhesion than the non-silicone-containing urethane acrylate).

- 20 This component is chosen to possess good thermal and hydrolytic properties and a low glass transition temperature, and to be somewhat non-yellowing.

- The polyether-based urethane acrylate comprises from about 35 percent to about 98 percent by weight of the matrix material composition, based on the total weight of the (a) through (d) ingredients. Preferably, the (a) component comprises from about 53 percent to about 87.5 percent, and more preferably about 64 percent to about 80 percent by weight of the composition, based upon the total weight of the (a) through (d) ingredients. If less than about 35 percent by weight of this component is used, the release properties of the matrix may suffer. If more than about 98 percent by weight is used, the viscosity of the composition may be undesirably high and swelling may occur when the matrix is exposed to certain solvents which may be used in the field and which may be absorbed by the matrix, such as ethanol, trichloroethane or isopropyl alcohol.

- 30 Examples of suitable urethane acrylates (a) include but are not limited to Ebecryl 4842 (equivalent to Chempol 19-4842), which is a silicone-modified compound, and Ebecryl 19-6264, which is not silicone-modified, and which contains about 15% by weight of 1,6-hexanediol diacrylate as a reactive solvent, both from Radcure Specialties, Inc., Louisville, Kentucky.

(B) The Monomer Having A Plurality of Acrylate or Methacrylate Groups

The second component of the matrix material is a monomer having a plurality of acrylate or methacrylate moieties.

- 40 This component, which may be difunctional or higher but which is preferably trifunctional, serves to increase the crosslink density of the cured coating and therefore to improve solvent resistance (by preventing absorption of solvent into the matrix) and to increase modulus. Examples of suitable components (b) include but are not limited to trimethylolpropane triacrylate; trimethylolpropane trimethacrylate; pentaerythritol triacrylate; pentaerythritol trimethacrylate; pentaerythritol tetraacrylate; pentaerythritol tetramethacrylate; trimethylolpropane propoxylate triacrylate; trimethylolpropane propoxylate trimethacrylate; trimethylolpropane ethoxylate triacrylate; trimethylolpropane ethoxylate trimethacrylate; glycerol propoxytri-
 45 acrylate; glycerol propoxytrimethacrylate; dipentaerythritol monohydroxy pentaacrylate; dipentaerythritol monohydroxy pentamethacrylate; C₆ - C₁₂ hydrocarbon diol diacrylates; C₆ - C₁₂ hydrocarbon diol dimethacrylates; and mixtures thereof. A preferred component (b) is trimethylolpropane triacrylate.

- 50 The monomer having a plurality of acrylate or methacrylate functionalities comprises from about 0.5 percent to about 35 percent by weight of the composition, based on the total weight of (a), (b), (c) and (d). Preferably, it comprises from about 10 percent to about 25 percent, and more preferably from about 15 percent to about 21 percent by weight of the composition, again based on total weight of (a) through (d). If less than about 0.5 percent by weight of component (b) is used, insufficient crosslink density, low modulus and poor solvent resistance may result; if more than about 35 percent is used, the cured composition may shrink to such an extent that adhesion may suffer (i.e., the matrix material may shrink away from the coated
 55 and inked optical fibers).

(C) The Alkyl Acrylate or Alkyl Methacrylate Monomer

The third component of the matrix material is an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 15 carbon atoms.

5 One of the key features of the present invention is its optimized adhesion level, i.e., it has a high enough adhesion level to remain adhered under virtually all use conditions yet low enough to render it easily strippable for splicing. Further, the adhesion level of the matrix to the coated and inked fibers is variable, as discussed in further detail hereinbelow, to meet different use conditions.

10 This third component (c) is instrumental in conferring release properties to the matrix material vis-a-vis the coated, inked optical fibers. As discussed above, it is necessary that a field worker is able to peel away the matrix material without removing the ink which identifies the underlying coated optical fibers, in order to splice the fibers together correctly. Furthermore, the inclusion of this third component increases the hydrolytic stability of the matrix material relative to that of the composition not including it. Thus, even in an embodiment, discussed infra, wherein increased (rather than decreased) adhesion is required, this
15 adhesion decreasing component should be used in addition to a further component that is capable of overriding this adhesion decreasing property, the adhesion-increasing component replacing a portion of the polyether urethane acrylate component (a).

In either embodiment, the adhesion level of matrix material to ink should fall within the range of between about 0.02 pounds per linear inch (lb./in.) and about 0.20 lb./in.; preferably between about 0.04
20 lb./in. and about 0.15 lb./in.; and more preferably between about 0.06 lb./in. and about 0.10 lb./in., as measured on a one-inch wide sample by a T-peel test, using an Instron, model 1122, at 23°C, with a 10 mm/min crosshead speed.

Examples of such monomers include but are not limited to stearyl acrylate; stearyl methacrylate; isooctyl acrylate; isooctyl methacrylate; lauryl acrylate; lauryl methacrylate; C₁₄ to C₁₅ hydrocarbon diol
25 diacrylates; C₁₄ to C₁₅ hydrocarbon diol dimethacrylates; caprolactone acrylate; caprolactone methacrylate; decyl acrylate; decyl methacrylate; isodecyl acrylate; isodecyl methacrylate; isobornyl acrylate; isobornyl methacrylate; and mixtures thereof. Of the above, those having straight chain alkyl groups of from 12 to 18 carbon atoms are preferred. Particularly preferred is stearyl acrylate, such as Sartomer SR-257 stearyl
acrylate from the Sartomer Company of West Chester, PA.

30 The alkyl-functional acrylate or methacrylate monomer (c) comprises from about 0.5 percent to about 20 percent by weight of the matrix material composition, based on the total of the weights of components (a) through (d). Preferably, it comprises from about 1 to about 14 percent by weight and more preferably about 3 to about 8 percent by weight of the composition, based on the total weight at (a), (b), (c) and (d). As mentioned supra, if less than about 0.5 percent by weight of this component is used, hydrolytic stability
35 may suffer. If more than 20 percent is used, crosslink density may be undesirably low, causing swelling of the matrix material due to solvent absorption when exposed to solvent in the field.

(D) The Photoinitiator

40 The fourth component of the matrix material is a photoinitiator. The necessity for this component depends on the envisioned mode of cure of the matrix material: if it is to be ultraviolet cured, a photoinitiator is needed; if it is to be cured by an electron beam, the material may comprise substantially no photoinitiator.

45 In the ultraviolet cure embodiment, the photoinitiator, when used in a small but effective amount to promote radiation cure, must provide reasonable cure speed without causing premature gelation of the matrix composition. Further, it must not interfere with the optical clarity of the cured matrix material. Still further, the photoinitiator must itself be thermally stable, non-yellowing, and efficient.

Suitable photoinitiators include, but are not limited to, the following: hydroxycyclohexylphenyl ketone; 50 hydroxymethylphenylpropanone; dimethoxyphenylacetophenone; 2-methyl-1-[4-(methyl thio) phenyl] -2-morpholinopropanone-1; 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan-1-one; 1-(4-dodecylphenyl)-2-hydroxy-2-methylpropan-1-one; 4-(2-hydroxyethoxy) phenyl-(2-hydroxy-2-propyl) ketone; diethoxyacetophenone; 2,2-di-sec-butoxyacetophenone; diethoxy-phenyl acetophenone; and mixtures of these.

The photoinitiator comprises from about 0 percent to about 10 percent by weight of the composition, based upon the weight of composition of the (a) through (d) ingredients (0 percent representing the electron
55 beam-curable embodiment). In the ultraviolet curable embodiment, the photoinitiator comprises from about 1 percent to about 10 percent by weight of the composition, based on (a) through (d). Preferably, the amount of photoinitiator, when used, is from about 1.5 percent to about 8.0 percent, and more preferably

from about 2.0 percent to about 7.0 percent by weight, based upon the total weight of the (a) through (d) ingredients. A particularly preferred photoinitiator is hydroxycyclohexylphenyl ketone, such as is supplied by Ciba-Geigy Corp., Ardsley, New York, as Irgacure 184.

The photoinitiator should be chosen such that cure speed, as measured in a dose versus modulus curve, of less than 1.0 J/cm², and preferably less than 0.5 J/cm², is required, when the photoinitiator is used in the designated amount.

OPTIONAL INGREDIENTS

The matrix material may also comprise one or more optional ingredients, discussed infra.

(E) Component Capable of Increasing Adhesion

As discussed above, a controlled adhesion level is an important parameter of the present invention. The adhesion level should again lie within the range of between about 0.02 lb./in. and about 0.20 lb./in., preferably between about 0.04 lb./in. and about 0.15 lb./in., and more preferably between about 0.06 lb./in. and about 0.10 lb./in. as measured by T-peel test, as described, supra. Functionally, this means that the matrix material is adherent enough to the coated and inked optical fibers so as not to separate therefrom under normal use conditions, yet releasable enough to separate easily from the coated, inked fibers clearly and without removing a substantial amount of ink therefrom during, for example, splicing operations.

In order to attain this desired amount of adhesion, it may be necessary to incorporate an agent capable of increasing the adhesion level of the matrix to a coated and inked optical fiber relative to the composition not incorporating it. This higher adhesion level might be necessary, for example, when an ink having relatively poor adhesion to the matrix material is used. This adhesion-increasing additive may be used in addition to or in lieu of a portion of the polyether-based urethane acrylate component (a).

The invention thus further comprises a process for adjusting the adhesive bond of a cured matrix material to coated and inked glass optical fibers by incorporating such adhesion-increasing component into the uncured matrix material.

When used, the adhesion-increasing component preferably comprises from about 1 to about 30 percent by weight, based on the total weight of components (a), (b), (c) and (d) only.

Suitable adhesion-increasing components include, but are not limited to, polyester-based aliphatic urethane acrylate oligomers, commercially available examples of which include Cargill 1512 oligomer, from Cargill, Inc., Minneapolis, Minnesota, and Ebecryl 284, from Radcure Specialties, Inc., Louisville, Kentucky.

(F) Stabilizers

Another optional class of components includes various stabilizers. To improve shelf life (storage stability) of the uncured coating, as well as to increase thermal and oxidative stability of the cured coating, one or more stabilizers may be included in the composition. Examples of suitable stabilizers include tertiary amines such as diethylethanolamine and trihexylamine; hindered amines; organic phosphites; hindered phenols; antioxidants; mixtures thereof; and the like. Some particular examples of antioxidants which can be used include octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate; thiodiethylene bis (3,5-di-tert-butyl-4-hydroxy) hydrocinnamate; and tetrakis [methylene (3,5-di-tert-butyl-4-hydroxyhydrocinnamate)] methane.

When a stabilizer is used, it may be incorporated in an amount from about 0.1 percent to about 3.0 percent, based on the weight of the (a) through (d) ingredients. Preferably, it is included in the range from about 0.25 percent to about 2.0 percent by weight, and more preferably in the range from about 0.5 percent to about 1.5 percent by weight, based on the total weight of the (a) through (d) ingredients. Desirable properties of a stabilizer include non-migration (probably enhanced by low polarity). A preferred stabilizer is thiodiethylene bis (3,5-di-tert-butyl-4-hydroxy) hydrocinnamate, such as Irganox 1035, from Ciba-Geigy Corporation, Ardsley, New York.

The resulting matrix material prepared in accordance with the invention should have a modulus of over about 1,000 psi, a viscosity of about 5,000 to about 9,000 cps at 23°C, a glass transition temperature of less than about -40°C (onset), low surface tack, fast cure and high thermal and hydrolytic stability.

THE OPTICAL FIBER RIBBON ASSEMBLY

The invention further relates to an optical fiber ribbon assembly. The ribbon assembly generally comprises a plurality of coated, inked optical fibers held in a fixed relationship, e.g., in a parallel and planar or other prescribed arrangement, and a radiation curable matrix material, in which the fibers are embedded, the matrix bonding the fibers in the desired arrangement. The matrix material has sufficient adhesion to the fibers to remain adhered thereto during use but is easily strippable there from without substantially damaging the integrity of an ink layer on the coated optical fibers.

The optical fibers which are part of the ribbon are those known in the art which are singly or dually coated before being bonded in the matrix material and which contain an ink layer on their surface, rendering each distinguishable from other fibers in the ribbon.

The optical fibers which are coated may comprise, for example, a glass core and a glass cladding layer. The core, for example, may comprise silica doped with oxides of germanium or phosphorus and the cladding, a pure or doped silicate such as a fluorosilicate. Alternately, the fibers may comprise a polymer clad silica glass core. Examples of such polymer claddings include organosiloxanes such as polydimethylsiloxane or a fluorinated acrylic polymer.

The fiber coatings are of the type known in the art and preferably are radiation, e.g., ultraviolet light, cured. The coating compositions may comprise a single or a dual layer and often contain cured acrylate or methacrylate components such as urethane diacrylates. A suitable secondary coating, for example, may comprise an aromatic polyester urethane acrylate; vinyl pyrrolidone; ethoxyethoxyethylacrylate; a photoinitiator; and stabilizer.

As discussed hereinabove, in order for the optical fiber ribbons to be spliced in a reasonably easy manner, it is desirable to identify the individual fibers by color coding them. It is possible to add a coloring agent to the outermost fiber coating layer; however, this is impractical because the coating will impart its color to the apparatus used to apply it, requiring numerous sets of drawing and coating apparatuses to accommodate each color of ink used.

Thus, it is more efficacious to ink over the optical fiber coating or coatings ink-containing layers of different colors, for individual fiber identification, by any means known in the art. The applied ink composition may be variable in nature but generally is vinylic and may comprise, for example, one or more organic or inorganic pigments; a vinyl copolymer; synthetic silica; and an organic solvent. As implied, *supra*, the precise nature of the ink composition will dictate the amounts and nature of the adhesion-affecting components in the matrix.

The matrix material which bonds the fibers is of the type which constitutes the present invention, i.e., one which comprises:

- (a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;
- (b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties;
- (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms; and
- (d) from about 0 percent to about 10 percent by weight of a photoinitiator, all of said percentages by weight being based on total weight of (a), (b), (c) and (d).

One kind of ribbon structure, and a cable made from such ribbon, is described in U.S. Patent 3,411,010 to Genähr et al., which is incorporated herein by reference.

PROCESS FOR PREPARING AN OPTICAL FIBER RIBBON

The invention comprises, in a further aspect, a process for preparing an optical fiber ribbon. Broadly, the process comprises mechanically arranging coated and inked fibers in a desired (i.e., generally planar and generally parallel) configuration; applying a matrix material composition about the fibers; and curing.

A suitable but non-limitative means for applying the matrix material to the fibers is as follows. Optical fibers which have been coated and inked over in the manner described hereinabove or in any manner known in the art may be used. The optical fibers may be mechanically arranged in the desired configuration (e.g., in a generally parallel, generally planar disposition relative to each other). The fibers may be held in the desired configuration, for example, by taping or otherwise holding the ends together. The matrix material may be applied about the fibers by any conventional means, i.e., by dipping the fibers into a vat of the material or pouring the material thereupon. Once the matrix has been applied substantially uniformly

about the fibers, it may be radiation cured, preferably either by ultraviolet light irradiation or via electron beam. Optionally, the composite may be flipped over, more matrix material applied thereto and the matrix again cured as above. The resulting ribbon contains the fibers bonded and secured in the desired disposition (i.e., generally parallel and generally planar). The adhesive bond of the cured matrix material to the coated and inked fibers may be adjusted by incorporation into the uncured compositions of a component capable of increasing the adhesive bond of the type discussed, supra, e.g., a polyester-based aliphatic urethane acrylate oligomer.

10 COATINGS FOR SUBSTRATES

Although the coating composition has been exemplified hereinabove for use as a matrix material for coated and inked optical fibers, it should be understood to be useful in any embodiment where it is desired to coat or bind a substrate (e.g., a flexible substrate) wherein the coating has an optimized adhesion level to the substrate and particularly an ink-covered substrate. Examples of such substrates include, but are not limited to, glass, metal or plastic. For example, composition may be used as a release coating for a glass or plastic substrate having a logo printed thereon, as may be used in electronics or other industries, to identify a supplier, or in any embodiment where it is desired to temporarily protect a printed surface. For example, a logo may be protected during shipping with such a release coating, which coating may be removed by the customer. Thus, the invention, stated more broadly, is a radiation curable coating composition for coating a substrate, the coating composition comprising:

- (a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;
- (b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties;
- (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms; and
- (d) from about 0 percent to about 10 percent by weight of a photoinitiator, all of the percentages by weight being based on total weight of (a), (b), (c) and (d).

EXAMPLES

The following Examples serve to further illustrate the invention. In these Examples and elsewhere throughout this application, all parts and percentages are by weight, on a dry solids basis, and all temperatures are in degrees centigrade (°C) unless expressly stated to be otherwise. In all of the Examples, cure speeds were measured with an International Light IL 745-A radiometer with model A309 light bug. In the Examples and elsewhere in this application, the terms "modulus" and "Instron modulus" refer to tensile modulus.

Unlike the remainder of the application, where percentages by weight refer to the total weight of the (a) through (d) components, parts by weight in the Examples refer to the total composition described in that Example, including all components. The optional ingredients are identified by an asterisk (*) in the Examples. The optional components may be necessary for use, if the exemplified coating is to meet the rigorous requirements for a commercially acceptable matrix for optical glass fiber ribbons.

EXAMPLE 1

A Coating Composition For A Flexible Substrate

A radiation-curable composition was formulated as follows:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate, from Radcure Specialties, Inc. Louisville, Kentucky (a)	72.28
Trimethylolpropane triacrylate (b)	17.82
SR-257 stearyl acrylate, from Sartomer Company, West Chester, PA (c)	4.95
Irgacure-184 hydroxycyclohexylphenyl ketone photoinitiator, from Ciba-Geigy, Ardsley, NY (d)	3.96
Irganox-1035 thiodiethylene bis (3,5-di-tert-butyl-4-hydroxy) hydrocinnamate stabilizer, from Ciba-Geigy *	0.99

The viscosity of the resulting (uncured) formulation was 6520 cps (at 25°C using a Brookfield viscometer, model LVT, at 6 rpm, # 34 spindle).

Shelf life as a function of change in viscosity over time of the uncured formulation was determined by weighing a 50 gram sample of the liquid into a 4-ounce glass jar with a lid and heating in a 200°F (93.3°C) oven for 16 hours. The change in viscosity was determined to be +8.3%.

The uncured material was applied to a substrate. The substrate comprised a flat glass sheet having taped on its surface an approximately seven-to nine-mil thick radiation-cured coating overprinted with an ink layer. The radiation-cured coating comprised the following:

<u>Ingredient</u>	<u>Parts by Weight</u>
vinyl pyrrolidone	11.5
ethoxyethoxyethylacrylate	11.5
Retarder/Stabilizer package	0.99
aromatic polyester urethane acrylate	74.01
2,2-dimethoxy-2-phenyl-acetophenone photoinitiator	2.0

The ink, which was orange in color, comprised pigment; a vinyl copolymer; synthetic silica and an organic solvent. It conferred an orange color to the coated, inked substrate.

The above composition was applied to the aforescribed coated and inked substrate as an about six-mil coating using a Bird applicator. It was ultraviolet cured in air at 0.7 J/cm² using a 200 watts per inch medium pressure mercury vapor lamp.

Adhesion of the cured matrix material was determined as follows. The coated substrate was cut into a 3 1/2 x 1 inch strip. A T-peel test was done using an Instron model 1122 with a crosshead speed of 10 mm/min at 23°C, range setting 100 g. An adhesion value of 0.075 (±0.011) lb./in. was measured.

The cured matrix had a glass transition temperature, as determined according to ASTM D-3418, of less than about -40°C (onset) and good surface tack.

Water absorption of the sample was measured as follows. The cured matrix material was equilibrated at 50% (±5%) relative humidity at 23°C (±2°C) for 48 hours. The sample was weighed and a weight "A" recorded. The sample was then soaked for 24 hours at 25°C in distilled water, then patted dry and weighed. This weight was recorded as "B". The sample was next placed in a vacuum oven under 10mm Hg pressure at 25°C for 24 hours, removed, and again equilibrated at 50% (±5%) relative humidity at 23°C (±2°C) for 48 hours and weighed. This third weight was recorded as "C". Percent water absorption measured as

$$\frac{B-C}{A} \times 100\%$$

was about 2.6%.

Solvent absorption of the sample was measured as follows. The cured matrix material (6-mil thickness) was cut in an approximately 2 x 2 inch section and weighed in a tared container. The film was immersed in ethanol for 5 minutes and then patted dry. It was returned to the tared container and reweighed after 5

was about 2.6%.

Solvent absorption of the sample was measured as follows. The cured matrix material (6-mil thickness) was cut in an approximately 2 x 2 inch section and weighed in a tared container. The film was immersed in ethanol for 5 minutes and then patted dry. It was returned to the tared container and reweighed after 5 minutes. The % solvent absorption was taken as the increase in weight divided by the initial weight x 100. The value was 14.2%.

Percent volatiles in the cured coating was determined by subjecting a sample cured and equilibrated as above to thermal gravimetric analysis (TGA) at 200 °C for 40 minutes in nitrogen atmosphere. A 5.12% volatiles weight loss was measured.

Oxidative induction temperature was measured by subjecting a 10 mg sample of the coating cured as above to differential scanning calorimetry in a pure oxygen atmosphere. The test was commenced at 100 °C and increased by 10 °C per minute until oxidation began, as evidenced by the beginning of a temperature exotherm. This point, the oxidative induction temperature, was measured at between about 190 °C and about 210 °C.

EXAMPLE 2

A Composition Having Good Adhesion and Viscosity but Slight Swelling

A formulation was made having the following components:

<u>Ingredients</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	82.0
1,6-hexanediol diacrylate (b)	9.0
SR-257 Stearyl acrylate (c)	5.0
Irgacure-184 photoinitiator (d)	4.0

The uncured formulation had a viscosity of 5750 cps at 25 °C using a Brookfield viscometer, model LVT, #34 spindle at 6 rpm and a Brookfield 74R temperature controller with a Thermosel.

The formulation was coated and cured in the manner of the previous Example. Modulus of the cured coating was determined to be 1,770 psi at 23±.5 °C, using an Instron Model 1122 fitted with a 50 kg load cell using a cross head speed of 5 mm/min and a chart speed of 200 mm/min.

Adhesion was determined in the following manner. A composition-coated and cured sheet substrate was cut into 0.8 inch-by-3 inch strips. Adhesion of the coating to the substrate was measured as in Example 1, and a value of 0.079 lb./in. was determined. Solvent absorption (ethanol) was determined, in the manner of Example 1, to be 28.8%.

EXAMPLE 3

A Formulation Having Lower Adhesion Properties

The following formulation was made up:

Ingredient	Parts by Weight
5 Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	82.0
Chemlink 2000, mixture of C ₁₄ and C ₁₅ hydrocarbon diol diacrylates from Sartomer Company (b)	9.0
SR-257 Stearyl acrylate (c)	5.0
Irgacure-184 photoinitiator (d)	4.0

10

When coated onto a substrate, cured, and subjected to the modulus and adhesion tests of the previous Examples, a modulus of 1,320 psi and adhesion level of 0.032 lb./in. were recorded.

15

EXAMPLE 4

A Formulation Having Somewhat High Adhesion

20

The following composition was formulated:

Ingredient	Parts by Weight
25 Ebecryl 264 aliphatic ether urethane acrylate, from Radcure Specialties, Inc. (a)	80.6
Radcure isobornyl acrylate (c)	15.3
Irgacure-184 photoinitiator (d)	4.1

30

The uncured composition had a viscosity at 25 °C of 8,550 cps, and the cured composition has a modulus of 50,800 psi, these properties measured as in the previous Examples.

Breakout was determined visually by observing the amount of ink removed from the substrate onto the cured matrix, and a value of about 1 was assigned, on a scale of 0 to 5, with 0 signifying that no ink was removed and 5 signifying that all the ink was removed from the substrate.

35

EXAMPLE 5

40

A Formulation Having somewhat High Adhesion and Higher Viscosity

The following composition was prepared:

Ingredients	Parts by Weight
45 Ebecryl 264 aliphatic ether urethane acrylate (a)	78.0
Photomer 4072, trimethylolpropane propoxylate triacrylate, from Henkel Corp., Ambler, PA (b)	18.0
50 Irgacure-184 photoinitiator (d)	4.0

The uncured composition had a viscosity of 11,920 cps, measured as in Example 1, and, when cured in the manner of previous Examples, the cured composition had a modulus of 55,600 psi and a breakout value of 1, all as measured as in the previous Examples.

55

Example 6

A Formulation Having Increased Adhesion

The following formulation was made:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	55.0
Cargill 1512, aliphatic polyester urethane acrylate in 25% hexanediol diacrylate solvent from Cargill, Inc., Minneapolis, MN*	30.0
1,6-hexanediol diacrylate (b)	11.0
Irgacure-184 photoinitiator (d)	4.0

The formulation which resulted was coated onto an inked (orange) substrate and cured in the manner described in earlier Examples. The adhesion level of the formulation was shown by a spot adhesion test (performed by curing a thin coat of the material on the inked substrate and peeling the cured material off by hand) to be high enough to pull most of the ink off of the substrate.

Example 7Another Formulation Having Increased Adhesion

The following formulation was devised:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	55.0
Ebecryl 284 aliphatic polyester urethane diacrylate in 1,6-hexanediol diacrylate (88% oligomer solids), from Radcure Specialties, Inc.* (parts by weight based on solids plus solvent)	28.0
1,6-hexanediol diacrylate (b)	13.0
Irgacure-184 photoinitiator (d)	4.0

The formulation was coated onto a substrate and cured and the adhesion level tested as in the previous Example. Again, the coating proved to have high enough adhesion to pull most of the ink off of the substrate.

EXAMPLE 8A Composition Having Low Adhesion

The following formulation was made:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	82.0
Tone M-100 caprolactone acrylate monomer, molecular weight 344, from Union Carbide Corporation, Danbury, CT (c)	14.0
Irgacure-184 photoinitiator (d)	4.0

The formulation was coated onto a white-inked substrate as above; adhesion was measured, in the manner of Example 1, to be 0.023 lb./in.

Example 9

Another Composition Having Low Adhesion and Low Modulus

The following formulation was made:

<u>Ingredients</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	82.0
Stearyl acrylate (c)	14.0
Irgacure-184 photoinitiator (d)	4.0

When cured in the manner of previous Examples, the cured composition had a modulus of 880 psi and an adhesion value of 0.023 lb./in., as measured in previous Examples.

Examples 10

Another Composition Having Low Adhesion

A formulation was made from the following:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	82.0
Ageflex FA-12 lauryl acrylate, from CPS Chemical Company, Inc., Old Bridge, NJ (c)	14.0
Irgacure-184 photoinitiator (d)	4.0

When cured and subjected to the modulus and adhesion tests of the previous Examples, a modulus of 738 psi and adhesion level of 0.031 lb./in. were noted.

Example 11

A Composition Having Acceptable Adhesion But Low Modulus

The following composition was prepared:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	81.0
Isobornyl acrylate (c)	15.0
Irgacure-184 photoinitiator (d)	4.0

The resulting uncured composition had a viscosity of 8,260 cps, measured as in Example 1. When cured as above, the material had a modulus of 900 psi and a breakout value, as described in Example 4, of 0.

Example 12

Another Composition Having Acceptable Adhesion and Good Modulus

The following composition was formulated:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	75.0
Photomer 4072 trimethylolpropane propoxylate triacrylate (b)	21.0
Irgacure-184 (d)	4.0

The resulting uncured composition had a viscosity of 9,670 cps, measured as in Example 1. When cured as in previous Examples, a modulus of 5,200 psi and breakout value of 0 were recorded.

Example 13

A Formulation Having Moderately High Adhesion

The following composition was made:

<u>Ingredient</u>	<u>Parts by Weight</u>
Ebecryl 4842 silicone modified aliphatic ether urethane acrylate (a)	82.0
1,6-hexanediol diacrylate (b)	14.0
Irgacure-184 (d)	4.0

The uncured composition had a viscosity of 5,180 cps, measured as in Example 1. When cured, a modulus of 3,672 psi was measured. After coating onto a white-inked substrate and curing the formulation in accordance with previous Examples, adhesion was determined to be 0.153 lb./in. according to the procedure described in Example 1.

COMPARATIVE EXAMPLE 1

A Composition Having Poor Breakout Properties

The following formulation was devised:

Ingredient	Parts by Weight
Ebecryl-284 aliphatic polyester urethane acrylate, from Radcure	66.0
Chemlink 2000 mixture of C ₁₄ -C ₁₅ hydrocarbon diol diacrylates, from Sartomer Company	15.0
Isobornyl acrylate, from Radcure	15.0
Irgacure-184 hydroxycyclophenyl ketone from Ciba Geigy	4.0

The above composition had an uncured viscosity of 2,600 cps, as measured using a Brookfield Viscometer, model LVT, at 25 °C, #34 spindle, at 12 rpm, and a Brookfield 74R temperature controller with a Thermosel. Uncured, the composition had a slightly yellow color.

The matrix was applied to an orange substrate of the type in Example 1 and ultraviolet cured in air at 0.7J/cm² using a 200 watts per inch medium pressure mercury vapor lamp. Modulus of the cured coating was determined to be 42,400 psi, and a breakout value of 4 was assigned, in accordance with the method of Example 4.

COMPARATIVE EXAMPLE 2A Composition Having Too High A Level of Adhesion

The following composition was formulated:

Ingredient	Parts by Weight
Cargill 1512 aliphatic ester urethane acrylate, in hexanediol diacrylate	75.76
Chemlink 2000 mixture of C ₁₄ and C ₁₅ diol diacrylates (b)	20.2
Irgacure-184 (d)	4.04

The uncured coating had a viscosity at 25 °C of 2,010 cps, measured as in Example 1.

The modulus at 23 °C was determined to be 80,000 psi. When applied to an orange substrate and cured as in previous Examples, the material was assigned a breakout value of 4.5.

COMPARATIVE EXAMPLE 3A Coating Having Poor Breakout

A mixture of equal parts by weight of the formulations of Example 4 and Comparative Example 2 was cured as above. A breakout value of 2 was assigned to the coating.

EXAMPLES 14-19Solvent Resistance of Bonded Ribbons: Formulations having Good Breakout and Marginal Solvent Resistance

Optical fiber ribbons were made from each of the formulations of Examples 2 and 13.

One-and-one-half inch strips of both kinds of ribbons were cut and placed in small vials to which were added, for each of the two types of matrix-containing ribbons, one of three solvents, respectively: isopropyl alcohol, ethyl alcohol and water. The so-treated samples were examined for appearance changes and breakout. The effects of the solvents on appearance and breakout are summarized in the following table:

Example No.	Example 2 Matrix	Example 13 Matrix	Solvent tested	Change in Appearance	Ease of breakout relative to non-solvent treated ribbon
14	X		Isopropyl alcohol	NO	Same
15		X	Isopropyl alcohol	NO	Easier
16	X		Ethanol	NO	Somewhat easier
17		X	Ethanol	NO	Easier
18	X		Water	NO	Not significantly easier
19		X	Water	NO	Not significantly easier

These results show solvent-sensitivity of the tested samples. This is believed to be related to poor crosslink density.

Examples 20-24

Solvent Sensitivity to Trichloroethane

Coated orange substrates were prepared using the coatings identified in the following Examples. Coating and curing was performed as described in preceding Examples:

Example 14 (for Example 20);

Example 2 (for Example 21);

Example 9 (for Example 22);

Example 3 (for Example 23); and

Example 10 (for Example 24).

One-inch wide strips of each coated substrate were soaked in trichloroethane for five minutes. With the exception of Example 20, each coated substrate delaminated at least partially as a result of the solvent exposure.

Example 25

Preparation of a Coated and Inked Substrate

A flat glass sheet was coated using a Bird applicator with a 6 mil coating of a commercially available, stabilized, UV-curable urethane acrylate oligomer-based composition.

The coating was UV-cured in air at 0.7J/cm² using a medium pressure 200 watts per inch mercury vapor lamp. This was in turn printed with a proprietary blue ink from Borden Packaging and Industrial Products, Cincinnati, Ohio, using a Meyer rod. The material of Example 1 was coated atop the inked substrate in the manner described in Example 1. Adhesion was measured to be 0.15 lbs/in. at 23°C in accordance with the methods of Example 1. It was observed that some of the ink was lifted from the substrate when the matrix material was removed therefrom.

CONCLUSION

A radiation-curable matrix material has been devised to possess a number of important qualities rendering it useful for various applications, e.g., for affixing coated and inked optical fibers in a ribbon configuration. The matrix material has a number of properties making it particularly suitable for such end

uses, these properties including moisture resistance; solvent resistance; thermal, oxidative and hydrolytic stability, and so forth.

However, one property of the matrix composition of the present invention, which is a valuable property, is its controlled and optimized adhesion level, which allows it to remain adhered to the (fiber) substrate during use, yet be strippable without substantial damage to the substrate, when required. This property is regulated by adjusting or controlling the use of either of the adhesion-decreasing component (i.e., the alkyl acrylate or methacrylate), or of the adhesion-increasing component (i.e., the polyester-based aliphatic urethane acrylate oligomer), or by a combination of the two, at appropriate levels to achieve the desired adhesion levels, in the range of 0.02 lb./in. to 0.20 lb./in.

While the invention has been disclosed in this patent application by reference to the details of preferred embodiments of the invention, it is to be understood that this disclosure is intended in an illustrative rather than in a limiting sense, as it is contemplated that modifications will readily occur to those skilled in the art, within the spirit of the invention and the scope of the appended claims.

Claims

1. A radiation-curable matrix material for affixing coated and inked optical fiber in a ribbon configuration, said matrix material comprising:
 - (a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;
 - (b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties;
 - (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms; and
 - (d) from about 0 percent to about 10 percent by weight of a photoinitiator;
 all of said percentages by weight being based on total weight of (a), (b), (c) and (d).
2. A radiation curable matrix material according to claim 1, wherein said polyether-based urethane acrylate is silicone-modified.
3. A radiation curable matrix material according to claim 1, wherein said monomer (b) is selected from the group consisting of trimethylolpropane triacrylate; trimethylolpropane trimethacrylate; pentaerythritol triacrylate; pentaerythritol trimethacrylate; pentaerythritol tetraacrylate; pentaerythritol tetramethacrylate; trimethylolpropane propoxylate triacrylate; trimethylolpropane propoxylate trimethacrylate; trimethylolpropane ethoxylate triacrylate; trimethylolpropane ethoxylate trimethacrylate; glycerol propoxytriacylate; glycerol propoxytrimethacrylate; dipentaerythritol monohydroxy pentaacrylate; dipentaerythritol monohydroxy pentamethacrylate; C₆ - C₁₂ hydrocarbon diol diacrylates; C₆ - C₁₂ hydrocarbon diol dimethacrylates; and mixtures thereof.
4. A radiation-curable matrix material according to claim 1, wherein said monomer (b) is trimethylolpropane triacrylate.
5. A radiation-curable matrix material according to claim 1, wherein said monomer (c) having an alkyl moiety comprising from 7 to 18 carbon atoms is selected from the group consisting of stearyl acrylate; stearyl methacrylate; isooctyl acrylate; isooctyl methacrylate; lauryl acrylate; lauryl methacrylate; C₁₄ to C₁₅ hydrocarbon diol diacrylates; C₁₄ to C₁₅ hydrocarbon diol dimethacrylates; caprolactone acrylate; caprolactone methacrylate; decyl acrylate; decyl methacrylate; isodecyl acrylate; isodecyl methacrylate; isobornyl acrylate; isobornyl methacrylate; and mixtures thereof.
6. A radiation-curable matrix material according to claim 1, wherein said photoinitiator (d) is selected from the group consisting of hydroxycyclohexylphenyl ketone; hydroxymethylphenylpropanone; dimethoxyphenylacetophenone; 2-methyl-1-[4-(methyl thio) phenyl]-2-morpholino-propanone-1; 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan -1-one; 4-(2-hydroxyethoxy) phenyl-(2-hydroxy-2-propyl) ketone; 1-(4-dodecyl phenyl)-2-hydroxy-2-methylpropan-1-one; diethoxyacetophenone; 2, 2-di-sec-butoxyacetophenone; diethoxy-phenyl acetophenone; and mixtures thereof.
7. A radiation-curable matrix material according to claim 6, wherein said photoinitiator is hydroxycyclohexylphenyl ketone.
8. A radiation-curable matrix material according to claim 1, additionally comprising from about 1 percent to about 30 percent by weight, based on total weight of (a), (b), (c) and (d), of a component (e) capable of increasing adhesion of said matrix material to a coated and inked optical fiber relative to the composition comprising only (a), (b), (c) and (d).
9. A radiation-curable matrix material according to claim 8, wherein said component (e) is a polyester based aliphatic urethane acrylate oligomer.

10. A radiation-curable matrix material according to claim 1, additionally comprising from about 0.1 percent to about 3 percent by weight, based on total weight of (a), (b), (c) and (d), of a stabilizer (f) selected from the group consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants; and mixtures thereof.
- 5 11. A radiation-curable matrix material according to claim 10, wherein said stabilizer (f) is thiodiethylene bis (3, 5-di-tert-butyl-4-hydroxy) hydrocinnamate,
12. A radiation-curable matrix material according to claim 8, additionally comprising from about 0.1 percent to about 3.0 percent by weight, based on total weight of (a), (b), (c) and (d) of a stabilizer (f) selected from the group consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants; and mixtures thereof.
- 10 13. A radiation-curable matrix material according to claim 12, wherein said stabilizer (f) is thiodiethylene bis (3, 5-di-tert-butyl-4-hydroxy) hydrocinnamate.
14. A radiation-curable matrix material according to claim 1 which is ultraviolet radiation curable and which comprises from about 1 percent to about 10 percent by weight of said photoinitiator (d).
- 15 15. A radiation-curable matrix material according to claim 1 which is electron beam-curable and which contains substantially no photoinitiator.
16. A radiation-curable matrix material for affixing coated and inked optical fibers in a ribbon configuration, said matrix material comprising:
 - (a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;
 - 20 (b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties and selected from the group consisting of trimethylolpropane triacrylate; trimethylolpropane trimethacrylate; pentaerythritol triacrylate; pentaerythritol trimethacrylate; pentaerythritol tetraacrylate; pentaerythritol tetramethacrylate; trimethylolpropane propoxylate triacrylate; trimethylolpropane propoxylate trimethacrylate; trimethylolpropane ethoxylate triacrylate; trimethylolpropane ethoxylate trimethacrylate; glycerol propoxytriacylate; glycerol propoxytrimethacrylate; dipentaerythritol monohydroxy pentaacrylate; dipentaerythritol monohydroxy pentamethacrylate; C₆ -C₁₂ hydrocarbon diol diacrylates; C₆ -C₁₂ hydrocarbon diol dimethacrylates; and mixtures thereof;
 - (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms, and selected from the group consisting of stearyl acrylate; stearyl methacrylate; isooctyl acrylate; isooctyl methacrylate; lauryl acrylate; lauryl methacrylate; C₁₄ to C₁₅ hydrocarbon diol diacrylates; C₁₄ to C₁₅ hydrocarbon diol dimethacrylates; caprolactone acrylate; caprolactone methacrylate; decyl acrylate; decyl methacrylate; isodecyl acrylate; isodecyl methacrylate; isobornyl acrylate; isobornyl methacrylate; and mixtures thereof; and
 - 30 (d) from about 0 percent to about 10 percent by weight of a photoinitiator that is selected from the group consisting of hydroxycyclohexylphenyl ketone; hydroxymethylphenylpropanone; dimethoxyphenylacetophenone; 2-methyl-1-[4-(methyl thio) phenyl]-2-morpholinopropanone-1; 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan -1-one; 4-(2-hydroxyethoxy) phenyl-(2-hydroxy-2-propyl) ketone; 1-(4-dodecyl phenyl)-2-hydroxy-2- methylpropan-1-one; diethoxyacetophenone; 2, 2-di-sec-butoxyacetophenone; diethoxy-phenyl acetophenone; and mixtures thereof;
 - 35 all of said percentages by weight being based on the total weight of (a), (b), (c) and (d).
17. A radiation-curable matrix material of claim 16 wherein said polyether-based urethane acrylate is silicone-modified.
18. A radiation-curable matrix material of claim 16 additionally comprising from about 1 percent to about 30 percent by weight, based on total weight of (a), (b), (c) and (d), of a component (e) capable of increasing
- 45 adhesion of said matrix material to a coated and inked optical fiber relative to the composition comprising only (a), (b), (c) and (d).
19. A radiation-curable matrix material of claim 18 wherein said component (e) is a polyester based aliphatic urethane acrylate oligomer.
20. A radiation-curable matrix material of claim 18 additionally comprising from about 0.1 percent to about 3 percent by weight, based on total weight of (a), (b), (c) and (d), of a stabilizer (f) selected from the group
- 50 consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants; and mixtures thereof.
21. A radiation-curable matrix material of claim 20 that is curable upon exposure to ultraviolet radiation and that comprises from about 1 percent to about 10 percent by weight of said photoinitiator (d).
- 55 22. A radiation-curable matrix material of claim 18 that is curable upon the application of an electron beam and that contains substantially no photoinitiator.
23. An ultraviolet radiation-curable matrix material for affixing coated optical fibers in a ribbon configuration, said matrix material comprising:

- (a) from about 53 percent to about 87.5 percent by weight of an aliphatic polyether-based urethane acrylate;
 (b) from about 10 percent to about 25 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties selected from the group consisting of trimethylolpropane triacrylate; trimethylolpropane trimethacrylate; pentaerythritol triacrylate; pentaerythritol trimethacrylate; pentaerythritol tetraacrylate; pentaerythritol tetramethacrylate; trimethylolpropane propoxylate triacrylate; trimethylolpropane propoxylate trimethacrylate; trimethylolpropane ethoxylate triacrylate; trimethylolpropane ethoxylate trimethacrylate; glycerol propoxytriacylate; glycerol propoxytrimethacrylate; dipentaerythritol monohydroxy pentaacrylate; dipentaerythritol monohydroxy pentamethacrylate; C₆ to C₁₂ hydrocarbon diol diacrylates; C₆ to C₁₂ hydrocarbon diol dimethacrylates, and mixtures thereof;
- (c) from about 1.0 percent to about 14 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms;
 (d) from about 1.5 percent to about 8 percent by weight of a photoinitiator;
 (e) from about 0 percent to about 30 percent by weight of a component capable of increasing adhesion of said matrix material to a coated and inked optical fiber relative to the composition comprising only (a), (b), (c) and (d); and
 (f) from about 0.25 percent to about 2 percent by weight of a stabilizer;
 all of said percentages by weight being based on the total weight of (a), (b), (c) and (d).
24. An ultraviolet radiation-curable matrix material for affixing coated and inked optical fibers in a ribbon configuration, said matrix material comprising:
- (a) from about 64 percent to about 80 percent by weight of a silicone-modified aliphatic polyether-based urethane acrylate;
 (b) from about 15 percent to about 21 percent by weight of trimethylolpropane triacrylate;
 (c) from about 3 percent to about 8 percent by weight of stearyl acrylate;
 (d) from about 2 percent to about 7 percent by weight of hydroxycyclohexylphenyl ketone photoinitiator; and
 (f) from about 0.5 percent to about 1.5 percent by weight of thiodiethylene bis (3, 5-di-tert-butyl-4-hydroxy) hydrocinnamate;
 all of said percentages by weight being based on total weight of (a), (b), (c) and (d).
25. An ultraviolet radiation curable matrix material according to claim 24, additionally comprising (e) from about 1 percent to about 30 percent by weight based on total weight of (a), (b), (c) and (d), of a polyester based aliphatic urethane acrylate oligomer.
26. An optical fiber ribbon assembly comprising:
 a plurality of optical fibers disposed in an arrangement in which the fibers are held in a fixed relationship; and
 a radiation curable matrix material bonding said fibers in said arrangement.
27. An optical fiber ribbon assembly according to claim 26 wherein said matrix material comprises:
 (a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;
 (b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties;
 (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms; and
 (d) from about 0 percent to about 10 percent by weight of a photoinitiator;
 all of said percentages by weight being based on total weight of (a), (b), (c) and (d).
28. An optical fiber ribbon assembly according to claim 27, wherein said polyether-based urethane acrylate (a) is silicone-modified.
29. An optical fiber ribbon assembly according to claim 27, wherein said monomer (b) is selected from the group consisting of trimethylolpropane triacrylate; trimethylolpropane trimethacrylate; pentaerythritol triacrylate; pentaerythritol trimethacrylate; pentaerythritol tetraacrylate; pentaerythritol tetramethacrylate; trimethylolpropane propoxylate triacrylate; trimethylolpropane propoxylate trimethacrylate; trimethylolpropane ethoxylate triacrylate; trimethylolpropane ethoxylate trimethacrylate; glycerol propoxytriacylate; glycerol propoxytrimethacrylate; dipentaerythritol monohydroxy pentaacrylate; dipentaerythritol monohydroxy pentamethacrylate; C₆ - C₁₂ hydrocarbon diol diacrylates; C₆ - C₁₂ hydrocarbon diol dimethacrylates; and mixtures thereof.
30. An optical fiber ribbon assembly according to claim 27, wherein said monomer (b) is trimethylolpropane triacrylate.
31. An optical fiber ribbon assembly according to claim 27, wherein said monomer having an alkyl moiety comprising from 7 to 18 carbon atoms (c) is selected from the group consisting of stearyl acrylate; stearyl

methacrylate; isooctyl acrylate; isooctyl methacrylate; lauryl acrylate; lauryl methacrylate; C₁₄ to C₁₅ hydrocarbon diol diacrylates; C₁₄ to C₁₅ hydrocarbon diol dimethacrylates; caprolactone acrylate; caprolactone methacrylate; decyl acrylate; decyl methacrylate; isodecyl acrylate; isodecyl methacrylate; isobornyl acrylate; isobornyl methacrylate; and mixtures thereof.

- 5 32. An optical fiber ribbon assembly according to claim 27, wherein said photoinitiator (d) is selected from the group consisting of hydroxycyclohexylphenyl ketone; hydroxymethylphenylpropanones dimethoxyphenylacetophenone; 2-methyl-1-[4-(methyl thio) phenyl]-2-morpholinopropanone-1; 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan-1-one; 4-(2-hydroxyethoxy) phenyl-(2-hydroxy-2-propyl) ketone; 1-(4-dodecyl phenyl)-2-hydroxy-2-methylpropan-1-one; diethoxyacetophenone; 2, 2-di-sec-butoxyacetophenone;
- 10 diethoxy-phenyl acetophenone; and mixtures thereof.
33. An optical fiber ribbon assembly according to claim 27, wherein said photoinitiator (d) is hydroxycyclohexylphenyl ketone.
34. An optical fiber ribbon assembly according to claim 27, additionally comprising from about 0.1 percent to about 30 percent by weight, based on total weight of (a), (b), (c) and (d), of a component (e) capable of
- 15 increasing adhesion of said matrix material to a coated and inked optical fiber relative to the composition comprising only (a), (b), (c) and (d).
35. An optical fiber ribbon assembly according to claim 34, wherein said component (e) is a polyester based aliphatic urethane acrylate oligomer.
36. An optical fiber ribbon assembly according to claim 27, additionally comprising from about 0.1 percent
- 20 to about 3 percent by weight, based on total weight of (a), (b), (c) and (d), of a stabilizer (f) selected from the group consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants; and mixtures thereof.
37. An optical fiber ribbon assembly according to claim 36, wherein said stabilizer (f) is thiodiethylene bis (3,5-di-tert-butyl-4-hydroxy) hydrocinnamate.
- 25 38. An optical fiber ribbon assembly according to claim 35, additionally comprising from about 0.1 percent to about 3 percent by weight, based on total weight of (a), (b), (c) and (d) of a stabilizer (f) selected from the group consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants, and mixtures thereof.
39. An optical fiber ribbon assembly according to claim 38, wherein said stabilizer (f) is thiodiethylene bis
- 30 (3,5-di-tert-butyl-4-hydroxy) hydrocinnamate.
40. An optical fiber ribbon assembly according to claim 27 wherein said optical fibers are coated before being bonded in said matrix material.
41. A ribbon assembly of claim 40 wherein the coating on said fibers comprises a cured acrylate-containing or a cured methacrylate-containing coating composition.
- 35 42. A ribbon assembly of claim 40 wherein said coated fibers are inked over their respective coatings with inks of different colors, for individual fiber identification.
43. A ribbon assembly of claim 41 wherein said coated fibers are colored over their respective coatings by applied vinyl inks of different colors, for individual fiber identification.
44. An optical fiber ribbon assembly comprising
- 40 a plurality of glass optical fibers disposed in a generally parallel arrangement; and an ultraviolet radiation-curable matrix material bonding said fibers in said arrangement, said matrix material comprising
- (a) from about 64 percent to about 80 percent by weight of a silicone-modified aliphatic polyether-based urethane acrylate;
- 45 (b) from about 15 percent to about 21 percent by weight of trimethylolpropane triacrylate;
- (c) from about 3 percent to about 8 percent by weight of stearyl acrylate;
- (d) from about 2 percent to about 7 by weight of hydroxycyclohexylphenyl ketone photoinitiator; and
- (f) from about 0.5 percent to about 1.5 percent by weight of thiodiethylene bis (3, 5-di-tert-butyl-4-hydroxy) hydrocinnamate;
- 50 all of said percentages by weight being based on total weight of (a), (b), (c) and (d).
45. An optical fiber ribbon assembly comprising:
- a plurality of glass optical fibers disposed in a generally planar and generally parallel arrangement, said optical fibers being coated with a coating comprising a cured acrylate-containing or a cured methacrylate-containing coating composition,
- 55 said coated fibers being inked over their respective coatings with inks of different respective colors, for individual fiber identification, and
- an ultraviolet radiation-curable matrix material disposed about said fibers and bonding them in said arrangement;

said matrix material comprising:

(a) from about 64 percent to about 80 percent by weight of a silicone-modified aliphatic polyether-based urethane acrylate;

(b) from about 15 percent to about 21 percent by weight of trimethylolpropane triacrylate;

5 (c) from about 3 percent to about 8 percent by weight of stearyl acrylate;

(d) from about 2 percent to about 7 by weight of hydroxycyclohexylphenyl ketone photoinitiator; and

(f) from about 0.5 percent to about 1.5 percent by weight of thiodiethylene bis (3, 5-di-tert-butyl-4-hydroxy) hydrocinnamate;

all of said percentages by weight being based on total weight of (a), (b), (c) and (d).

10 46. A radiation-curable coating composition for coating a substrate, said coating composition comprising:

(a) from about 35 percent to about 98 percent by weight of an aliphatic polyether-based urethane acrylate;

(b) from about 0.5 percent to about 35 percent by weight of a monomer having a plurality of acrylate or methacrylate moieties;

15 (c) from about 0.5 percent to about 20 percent by weight of an acrylate or methacrylate monomer having an alkyl moiety comprising from 7 to 18 carbon atoms; and

(d) from about 0 percent to about 10 percent by weight of a photoinitiator;

all of said percentages by weight being based on total weight of (a), (b), (c) and (d).

47. A radiation-curable coating composition according to claim 46, wherein said polyether-based urethane acrylate is silicone-modified.

20 48. A radiation-curable coating composition according to claim 46, wherein said monomer (b) is selected from trimethylolpropane triacrylate; trimethylolpropane trimethacrylate; pentaerythritol triacrylate; pentaerythritol trimethacrylate; pentaerythritol tetraacrylate; pentaerythritol tetramethacrylate; trimethylolpropane propoxylate triacrylate; trimethylolpropane trimethacrylate; trimethylolpropane ethoxylate triacrylate; trimethylolpropane ethoxylate trimethacrylate; glycerol propoxytriacylate; glycerol propoxytrimethacrylate; dipentaerythritol monohydroxy pentaacrylate; dipentaerythritol monohydroxy pentamethacrylate; C₆ -C₁₂ hydrocarbon diol diacrylates; C₆ -C₁₂ hydrocarbon diol dimethacrylates; and mixtures thereof.

25 49. A radiation-curable coating composition according to claim 46, wherein said monomer having an alkyl moiety comprising from 7 to 18 carbon atoms (c) is selected from the group consisting of stearyl acrylate; stearyl methacrylate; isooctyl acrylate; isooctyl methacrylate; lauryl acrylate; lauryl methacrylate; C₁₄ to C₁₅ hydrocarbon diol diacrylates; C₁₄ to C₁₅ hydrocarbon diol dimethacrylates; caprolactone acrylate; caprolactone methacrylate; decyl acrylate; decyl methacrylate; isodecyl acrylate; isodecyl methacrylate; isobornyl acrylate; isobornyl methacrylate; and mixtures thereof.

30 50. A radiation-curable coating composition according to claim 46, wherein said photoinitiator (d) is selected from the group consisting of hydroxycyclohexylphenyl ketone; hydroxymethylphenylpropanone; dimethoxyphenylacetophenone; 2-methyl-1-[4-(methyl thio) phenyl]-2-morpholino-propanone-1; 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan-1-one; 4-(2-hydroxyethoxy) phenyl-(2-hydroxy-2-propyl) ketone; 1-(4-dodecyl phenyl)-2-hydroxy-2-methylpropan-1-one; diethoxyacetophenone; 2, 2-di-sec-butoxyacetophenone; diethoxy-phenyl acetophenone; and mixtures thereof.

35 51. A radiation-curable coating composition according to claim 46, additionally comprising from about 1 percent to about 30 percent by weight, based on total weight of (a), (b), (c) and (d), of a component (e) capable of increasing adhesion of said matrix material to a coated and inked optical fiber relative to the composition comprising only (a), (b), (c) and (d).

52. A radiation-curable coating composition according to claim 51, wherein said component (e) is a polyester based aliphatic urethane acrylate oligomer.

45 53. A radiation-curable coating composition according to claim 46, additionally comprising from about 0.1 percent to about 3 percent by weight, based on total weight of (a), (b), (c) and (d), of a stabilizer (f) selected from the group consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants; and mixtures thereof.

50 54. A radiation-curable coating composition according to claim 51, additionally comprising from about 0.1 percent to about 3.0 percent by weight, based on total weight of (a), (b), (c) and (d) of a stabilizer (f) selected from the group consisting of tertiary amines; hindered amines; organic phosphites; hindered phenols; antioxidants; and mixtures thereof.

55 55. A radiation-curable coating composition according to claim 46, which is ultraviolet radiation-curable and which comprises from about 1 percent to about 10 percent by weight of said photoinitiator (d).

56. A radiation-curable coating composition according to claim 46, which is electron beam-curable and which is substantially free of photoinitiator.

57. A process for preparing an optical fiber ribbon comprising:
mechanically arranging optical fibers in a generally parallel arrangement;

applying about said fibers the matrix material of claim 1; and
curing said matrix material, thereby securing said fibers in said arrangement.

58. A process according to claim 57 wherein said composition comprises a photoinitiator, and said curing is effected via ultraviolet irradiation.

5 59. A process according to claim 57 wherein said composition is substantially free of photoinitiator, and said curing is effected via electron beam irradiation.

60. A process for preparing an optical fiber ribbon comprising:
mechanically aligning coated optical fibers in a generally parallel disposition relative to each other;
applying about said fibers the matrix material of claim 16; and

10 curing said matrix material, thereby securing said fibers in said disposition.

61. A process according to claim 38 wherein said composition comprises a photoinitiator, and said curing is effected via ultraviolet irradiation.

62. A process according to claim 38 wherein said curing is effected via electron beam irradiation.

63. A process of claim 60 wherein said coated optical fibers are coated with a coating comprising a cured
15 acrylate-containing or a cured methacrylate-containing composition.

64. A process of claim 63 wherein said coated fibers are inked over their respective coatings with inks of different respective colors, for individual fiber identification.

65. A process for preparing an optical fiber ribbon from a plurality of coated and inked glass optical fibers, wherein said optical fibers are covered with a coating comprising a cured acrylate-containing or a cured
20 methacrylate-containing coating composition, and wherein said coated fibers are inked over their respective coatings with inks of different respective colors, for individual fiber identification,
said process comprising:

aligning said plurality of coated, inked fibers in a generally planar, generally parallel disposition;
disposing matrix material according to claim 24 about said fibers; and

25 curing said matrix material to bond said fibers in said disposition.

66. A process of claim 65 wherein said matrix material further comprises from about 1% to about 30% by weight of a polyester based urethane acrylate oligomer, based on the total weight of (a), (b), (c) and (d).

67. A process according to claim 65 wherein said curing is effected via ultraviolet irradiation.

68. A process according to claim 65 wherein said curing is effected via electron beam irradiation.

30 69. A process for adjusting the adhesive bond of a cured, radiation-curable matrix material, to coated and inked glass optical fibers to which said cured matrix material is bonded, wherein said optical fibers are coated with a coating comprising a cured acrylate-containing or a cured methacrylate-containing coating composition,

said coated fibers are colored by the application over their respective coatings of inks of different respective
35 colors, for individual fiber identification, and

said matrix material comprises a radiation-curable matrix material of claim 23,

said process comprising incorporating in said uncured matrix material a component that is capable of increasing said adhesive bond.

40 70. The process of claim 69 wherein said component comprises a polyester based aliphatic urethane acrylate oligomer.

71. A process for adjusting the adhesive bond of a cured, radiation-curable matrix material, to coated and inked glass optical fibers to which said cured matrix material is bonded, wherein said optical fibers are coated with a coating comprising a cured acrylate-containing or a cured methacrylate-containing coating composition,

45 said coated fibers are colored by the application over their respective coatings of inks of different respective colors, for individual fiber identification, and

said matrix material comprises a radiation-curable, matrix material of claim 24,

said process comprising incorporating in said uncured matrix material a component that is capable of increasing said adhesive bond.

50 72. The process of claim 71 wherein said component comprises from about 1% to about 30% by weight of a polyester based aliphatic urethane acrylate oligomer, based on the total weight of (a), (b), (c) and (d).